



CERTIFICATE OF TESTING

For The Account Of: **Pollack**
 150 Varick Street
 New York, NY 10013-1218
 Contact: Larry Hoysic

DATE: July 14, 2005 CERTIFICATE (ORDER) NO.: 13560

CLIENT'S IDENTIFICATION: A New Leaf 2252

CAL117, Section E, Part I - Upholstery Fabrics (CS 191-53) Plain Surface

Specimen	<u>Flame Spread Warp</u> (seconds)	Without Nap (Plain Surface) FACE	Specimen	<u>Flame Spread Warp</u> (seconds)	Without Nap (Plain Surface) BACK
1	DNI	X	1	DNI	X
2	DNI	X	2	DNI	X
3	DNI	X	3	DNI	X
4	DNI	X	4	DNI	X
5	DNI	X	5	DNI	X

Specimen	<u>Flame Spread Fill</u> (seconds)	Without Nap (Plain Surface) FACE	Specimen	<u>Flame Spread Fill</u> (seconds)	Without Nap (Plain Surface) BACK
1	DNI	X	1	DNI	X
2	DNI	X	2	DNI	X
3	DNI	X	3	DNI	X
4	DNI	X	4	DNI	X
5	DNI	X	5	DNI	X

- **DNI - Did not ignite when exposed to test ignition source**
- **IBE - Ignited but extinguished before burning through stop cord.**
- **SF - Surface flash only; stop cord not burned & no burning/charring/fusing of the base fabric.**
- **TSF - Timed surface flash; stop cord burned, but no burning/charring/fusing of the base fabric.**

Requirements: With nap - Minimum flame spread of any individual specimens shall be less than 7 seconds.

Requirements: Without nap - Minimum flame spread of any individual specimens shall be less than 3.5 seconds.

Conclusion: The above results indicate **COMPLIANCE** with the stated requirements.

I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by California Technical Bulletin 117, Section E, Part I Upholstered Fabrics dated January 1980.

Lab Manager: Sallie Cotey

Jennifer Friend
 Lab Technician: Jennifer Friend

F-310-A