



## CERTIFICATE OF TESTING

For The Account Of: **Pollack**  
 150 Varick Street  
 New York, NY 10013  
 Contact: Larry Hoysic

DATE: August 9, 2005      CERTIFICATE (ORDER) NO.: 13707

CLIENT'S IDENTIFICATION: Correggia 4093

**CAL117, Section E, Part I - Upholstery Fabrics (CS 191-53) Plain Surface**

Specimen	<u>Flame Spread Warp</u> (seconds)	Without Nap (Plain Surface) <b>FACE</b>	Specimen	<u>Flame Spread Warp</u> (seconds)	Without Nap (Plain Surface) <b>BACK</b>
1	DNI	X	1	DNI	X
2	DNI	X	2	DNI	X
3	DNI	X	3	DNI	X
4	DNI	X	4	DNI	X
5	DNI	X	5	DNI	X

Specimen	<u>Flame Spread Fill</u> (seconds)	Without Nap (Plain Surface) <b>FACE</b>	Specimen	<u>Flame Spread Fill</u> (seconds)	Without Nap (Plain Surface) <b>BACK</b>
1	DNI	X	1	DNI	X
2	DNI	X	2	DNI	X
3	DNI	X	3	DNI	X
4	DNI	X	4	DNI	X
5	DNI	X	5	DNI	X

- **DNI** - Did not ignite when exposed to test ignition source
- **IBE** - Ignited but extinguished before burning through stop cord.
- **SF** - Surface flash only; stop cord not burned & no burning/charring/fusing of the base fabric.
- **TSF** - Timed surface flash; stop cord burned, but no burning/charring/fusing of the base fabric.

**Requirements: With nap** - Minimum flame spread of any individual specimens shall be less than 7 seconds.

**Requirements: Without nap** - Minimum flame spread of any individual specimens shall be less than 3.5 seconds.

**Conclusion:** The above results indicate **COMPLIANCE** with the stated requirements.

I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by California Technical Bulletin 117, Section E, Part I Upholstered Fabrics dated January 1980.

Lab Manager: Sallie Cotey

*Jennifer Friend*  
 Lab Technician: Jennifer Friend

F-310-A