

**CERTIFICATE OF TESTING**

For The Account Of: **Pollack**  
 150 Varick St.  
 New York, NY 10013

DATE: July 26, 2006                      CERTIFICATE (ORDER) NO.: 16843

CLIENT'S IDENTIFICATION: Melange #4107

**CAL117, Section E, Part I - Upholstery Fabrics (CS 191-53) Plain Surface**

Specimen	<u>Flame Spread Warp</u> (seconds)	Without Nap (Plain Surface)		Specimen	<u>Flame Spread Warp</u> (seconds)	Without Nap (Plain Surface)	
		<b>FACE</b>				<b>BACK</b>	
1	DNI	X		1			
2	DNI	X		2			
3	DNI	X		3			
4				4	DNI		X
5				5	DNI		X

Specimen	<u>Flame Spread Fill</u> (seconds)	Without Nap (Plain Surface)		Specimen	<u>Flame Spread Fill</u> (seconds)	Without Nap (Plain Surface)	
		<b>FACE</b>				<b>BACK</b>	
1	DNI	X		1			
2	DNI	X		2			
3	DNI	X		3			
4				4	DNI		X
5				5	DNI		X

- **DNI - Did not ignite when exposed to test ignition source**
- **IBE - Ignited but extinguished before burning through stop cord.**
- **SF - Surface flash only; stop cord not burned & no burning/charring/fusing of the base fabric.**
- **TSF - Timed surface flash; stop cord burned, but no burning/charring/fusing of the base fabric.**


**Requirements: With nap** - Minimum flame spread of any individual specimens shall be less than 7 seconds.

**Requirements: Without nap** - Minimum flame spread of any individual specimens shall be less than 3.5 seconds.

**Conclusion:** The above results indicate **COMPLIANCE** with the stated requirements.

I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by California Technical Bulletin 117, Section E, Part I Upholstered Fabrics dated January 1980.

Lab Manager: Sallie Cotey

  
 Lab Technician: Jennifer Friend