



Textile Testing

553 76th Street · Byron Center, MI 49315 Phone: 616.559.6123 Fax: 616.559.6119

Report Number: 30010

Date: 8-26-2008

For the Account Of: Pollack
150 Varick Street
New York, NY 10013
Contact: Larry Hoysic

Client's Identification: Rebound 4131

Test Performed California Technical Bulletin 117, Section E (CPSC 16 CFR 1610 – CS 191-53) Upholstery Fabrics

TEST DATA

Plain Surface Raised Surface

| Specimen | Flame Spread | Flame Spread |
|----------|-------------------------------|-------------------------------|
| | <u>Warp Face</u> (seconds) | <u>Warp Back</u> (seconds) |
| 1 | DNI | |
| 2 | DNI | |
| 3 | DNI | |
| 4 | | DNI |
| 5 | | DNI |

| Specimen | Flame Spread | Flame Spread |
|----------|-------------------------------|-------------------------------|
| | <u>Fill Face</u> (seconds) | <u>Fill Back</u> (seconds) |
| 1 | DNI | |
| 2 | DNI | |
| 3 | DNI | |
| 4 | | DNI |
| 5 | | DNI |

ABBREVIATIONS USED

- DNI** Did not ignite when exposed to test ignition source
- IBE** Ignited but extinguished before burning through stop cord
- SF** Surface flash only; stop cord not burned & no burning/charring/fusing of the base fabric
- TSF** Timed surface flash; stop cord burned, but no burning/charring/fusing of the base fabric


ACCEPTANCE CRITERIA

1. **With nap** - Minimum flame spread of any individual specimens shall be 7 seconds.
2. **Without nap** - Minimum flame spread of any individual specimens shall be 3.5 seconds.

CONCLUSION Based on the above Results and Acceptance Criteria, the item tested:

- Complies
- Does Not Comply

CERTIFICATION: I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.


Authorized Signature

