Textile Testing

553 76th Street · Byron Center, MI 49315 Phone: 616.559.6123 Fax: 616.559.6119

Report Number: 39300

Date: 3-9-10

For the Account Of:

Pollack

150 Varick St

New York, NY 10013

Contact:

Larry Hoysic

Client's Identification:

Linen Velour 5073

Test Performed

California Technical Bulletin 117, Section E (CPSC 16 CFR 1610 - CS 191-53) Upholstery

Fabrics

TEST DATA

☐ Plain Surface

Cunadiman	Flame Spread Warp Face	Flame Spread Warp Back
Specimen	(seconds)	(seconds)
1	DNI	
2	DNI	
3	DNI	
4		DNI
5		DNI

***************************************	Flame Spread	Flame Spread
	<u>Fill Face</u>	Fill Back
Specimen	(seconds)	(seconds)
1	DNI	
2	DNI	
3	DNI	
4		DNI
5		DNI

ABBREVIATIONS USED

DNI Did not ignite when exposed to test ignition source

IBE Ignited but extinguished before burning through stop cord

Surface flash only; stop cord not burned & no burning/charring/fusing of the base fabric SF **TSF**

Timed surface flash; stop cord burned, but no burning/charring/fusing of the base fabric

ACCEPTANCE CRITERIA

- 1. With nap Minimum flame spread of any individual specimens shall be 7 seconds.
- 2. Without nap Minimum flame spread of any individual specimens shall be 3.5 seconds.

CONCLUSION

Based on the above Results and Acceptance Criteria, the item tested:

□ Complies

☐ Does Not Comply

CERTIFICATION: I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature //