



Textile Testing

553 76th Street · Byron Center, MI 49315 Phone: 616.559.6123 Fax: 616.559.6119

Report Number: 26837

Date: 3-18-2008

For the Account Of: Pollack
150 Varick Street
New York, NY 10013
Contact: Larry Hoysic

Client's Identification: Stepping Stone 6041

Test Performed California Technical Bulletin 117, Section E (CPSC 16 CFR 1610 – CS 191-53) Upholstery Fabrics

TEST DATA

Plain Surface Raised Surface

Specimen	Flame Spread	Flame Spread
	<u>Warp Face</u> (seconds)	<u>Warp Back</u> (seconds)
1	DNI	
2	DNI	
3	DNI	
4		DNI
5		DNI

Specimen	Flame Spread	Flame Spread
	<u>Fill Face</u> (seconds)	<u>Fill Back</u> (seconds)
1	DNI	
2	DNI	
3	DNI	
4		DNI
5		DNI

ABBREVIATIONS USED

- DNI** Did not ignite when exposed to test ignition source
- IBE** Ignited but extinguished before burning through stop cord
- SF** Surface flash only; stop cord not burned & no burning/charring/fusing of the base fabric
- TSF** Timed surface flash; stop cord burned, but no burning/charring/fusing of the base fabric

ACCEPTANCE CRITERIA

1. **With nap** - Minimum flame spread of any individual specimens shall be 7 seconds.
2. **Without nap** - Minimum flame spread of any individual specimens shall be 3.5 seconds.

CONCLUSION Based on the above Results and Acceptance Criteria, the item tested:

- Complies
- Does Not Comply

CERTIFICATION: I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature 