

Received: 11/12/2003	Completed: 12/03/2003	Letter: C3	rb	P.O.#: MFG-005716	Test Report #:	2-48251-0-03
----------------------	-----------------------	------------	----	-------------------	----------------	--------------

Client's Identification: **Suede Charade 9908**

Key Test: ASTM E 84

715

Tel:

Ext:

Fax:

PC: ME

CODE: 7506506005501-4

TEST PERFORMED: ASTM E 84 - Standard Test Method for Surface Burning Characteristics of Building Materials \*

APPROXIMATE THICKNESS OF SPECIMEN (as measured by Govmark): 0.034"

PRODUCT CATEGORY:  Textile Type Product  
 Vinyl Type Product  
 Other than Textile Type or Vinyl Type Product:

\* Note: Textile or vinyl wallcoverings classified by this procedure are limited to use in sprinklered areas in certain public occupancies. If textile or vinyl wallcoverings are used in non-sprinklered areas, a room/corner fire test is mandated.

SPECIMEN CONDITIONING: The item tested was placed in a conditioned atmosphere of 73.4°F ± 5°F, and 50% ± 5% RH until equilibrium was reached.

SPECIMEN MOUNTING:

Adhered: The test specimen was bonded to three 1/4" IRC (Inorganic Reinforced Cement) boards (a cement asbestos substitute) to form a test specimen the face of which was 20" x 24'.

Unadhered: The 20" x 24' specimen was not adhered to any substrate. Instead, it was laid over a 2" hexagonal wire mesh screen and 1/4" rods.

RESULTS:

Flame Spread Index	Smoke Developed
15	55

CODE CLASSIFICATION SYSTEM:	Flame Spread Index	Smoke Developed
Class I or A	0 - 25	450 or Less
Class II or B	26 - 75	450 or Less
Class III or C	76 - 200	450 or Less

CONCLUSION: Based on the above results and Code Classification System the item tested is assigned a:

- Class I or A rating
- Class II or B rating
- Class III or C rating
- Unrated

Received: 11/12/2003	Completed: 12/03/2003	Letter: C3	rb	P.O.#: MFG-005716	Test Report #:	2-48251-0-03
----------------------	-----------------------	------------	----	-------------------	----------------	--------------

Client's Identification **Suede Charade 9908**

Key Test: ASTM E 84

715

Tel:

Ext:


Fax:

REMARKS: None.

DATA SUMMARY:

Time to Ignition: 0.10 minutes  
Maximum Flame Spread "Distance": 3.17 feet  
Maximum Flame Spread "Time": 0.48 minutes

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by ASTM E 84.



-----  
AUTHORIZED SIGNATURE

THE GOVMARK ORGANIZATION, INC. CT /rb

(Page 2 of 2)

Received: 11/12/2003 Completed: 12/03/2003 Letter: B1 rb P.O.#: MFG-005716 Test Report #: 2-48250-0-01

Client's Identification: **Suede Charade 9908**

Key Test: ASTM E 84 715

Tel: \_\_\_\_\_ Ext: \_\_\_\_\_  
Fax: \_\_\_\_\_

PC: ME CODE: 7506506005501-4

TEST PERFORMED: ASTM E 84 - Standard Test Method for Surface Burning Characteristics of Building Materials \*

APPROXIMATE THICKNESS OF SPECIMEN (as measured by Govmark): 0.035"

PRODUCT CATEGORY:  Textile Type Product  
 Vinyl Type Product  
 Other than Textile Type or Vinyl Type Product:

\* Note: Textile or vinyl wallcoverings classified by this procedure are limited to use in sprinklered areas in certain public occupancies. If textile or vinyl wallcoverings are used in non-sprinklered areas, a room/corner fire test is mandated.

SPECIMEN CONDITIONING: The item tested was placed in a conditioned atmosphere of 73.4°F ± 5°F, and 50% ± 5% RH until equilibrium was reached.

SPECIMEN MOUNTING:

Adhered: The test specimen was bonded to three 1/4" IRC (Inorganic Reinforced Cement) boards (a cement asbestos substitute) to form a test specimen the face of which was 20" x 24'.

Unadhered: The 20" x 24' specimen was not adhered to any substrate. Instead, it was laid over a 2" hexagonal wire mesh screen and 1/4" rods.

RESULTS:

Flame Spread Index	Smoke Developed
-----	-----
5	50

CODE CLASSIFICATION SYSTEM:	Flame Spread Index	Smoke Developed
	-----	-----
Class I or A	0 - 25	450 or Less
Class II or B	26 - 75	450 or Less
Class III or C	76 - 200	450 or Less

CONCLUSION: Based on the above Results and Code Classification System the item tested is assigned a:

Class I or A rating  
 Class II or B rating  
 Class III or C rating  
 Unrated

