



**Textile Testing**

553 76<sup>th</sup> Street · Byron Center, MI 49315 Phone: 616.559.6123 Fax: 616.559.6119

Report Number: 35522

Date: 6-24-2009

For the Account Of: Pollack  
150 Varick street  
New York, NY 10013

Contact: Maryanne Solensky

Client's Identification: Zamboni – olive oil

**Test Performed NFPA 260 Standard Methods of Tests and Classification System for Cigarette Ignition Resistance of Components of Upholstered Furniture – 2009: Fabric Cover Test and UFAC Fabric Classification Test Method – 1990**

**TEST DATA**

Specimen #	Char Length (inches)
1	SE
2	SE
3	SE

\*\*SE= Self Extinguished

**NOTES**

**Test Conditions:** 70 ±2°F, 65 ±2% Relative Humidity

**ACCEPTANCE CRITERIA**

1. If the test specimen has no ignition, or if no individual specimen yields a vertical char of 44 mm (1.75 in.) or less, the fabric is classified a UFAC and NFPA Class I cover fabric.
2. If the vertical char of the test specimen greater than 45 mm (1.75 in.), the fabric is classified a UFAC Class II cover fabric.
3. If an obvious ignition of the polyurethane substrate occurs on the test assembly, the fabric is classified a UFAC Class II cover fabric.

**CONCLUSION** Based on the above Results and Acceptance Criteria, the item tested is:

- Class I
- Class II

CERTIFICATION: I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Charon McDaniel